

PROCESSING GUIDE

ALCOM[®] PC LG is a Polycarbonate, an amorphous thermoplastic, with special additives for an optimal light guiding.

PRE-TREATMENT

ALCOM[®] PC LG is a hygroscopic polymer. Due to absorption of moisture from the air, drying is mandatory in order to avoid material degradation and surface defects. For specific filled products see corresponding Technical Data Sheet.

PROCESSING

ALCOM[®] PC LG may be processed on all standard injection moulding machines. Wear protected plasticising units for reinforced compounds are advised. Hotrunner with torpedo or hot tip are not recommended. ALCOM[®] PC LG products are more sensible to shearing – try to avoid small gates and process without excessive stress. For longer production interruptions, set cylinder heaters to about 170 °C and ensure heating.



¹ Guide values. Standard starting profile might be in the middle.

		Unit	Notes
Properties			
Polymer abbreviation		PC	
Density (ISO 1183)	g/cm ³	1.18 – 1.20 (see Technical Data Sheet)	
Injection Machinery			
Screw stroke	Metering stroke between 1 x D and 3 x D		
Screw type	Three zone screw with L/D ratio 18:1 to 22:1		
Nozzle type	Open or shut-off possible		
Hopper type	Standard		
Pre-processing			
Storage		Dry, protected from heat and light	
Dryer type		Air circulating	Dry air
Drying time	h	4 – 12	3 – 4
Drying temperature	°C	120	
Permissible moisture content	%	< 0.02	
Processing Conditions			
Melt temperature range	°C	280 – 310	
Mould temperature range	°C	80 – 110	
Coolant		Water	
Throughput coolant		To ensure turbulent flow	
Peripheral screw speed	mm/s	50 – 300, e.g. screw speed of 40rpm with a screw diameter of 50mm	
Back pressure (specific)	bar	50 – 100	
Residence time	minutes	4 – 8	
Injection speed		Profile for constant flow front speed	
Shrinkage²			
Shrinkage range (ISO 294-4)	%	0.5 – 0.9	

² Shrinkage is influenced by the part geometry, the wall thickness of the moulding, the position and size of the gate and the processing parameters.

HEAD OFFICE

ALBIS PLASTIC GmbH
 Mühlenhagen 35 · 20539 Hamburg
 Telephone: +49 40 7 81 05-0
 Fax: +49 40 7 81 05-361
 info@albis.com · www.albis.com

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended. The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations.

NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.