

Polyethylene

Grades Used in Injection Molding Applications (1/2)

PROPERTIES	PHYSICAL			MECHANICAL						THERMAL	ESCR	SPECIFIC CHARACTERISTICS AND TYPICAL CUSTOMER APPLICATIONS	
	Density 23°C	Melt Flow Rate		Tensile Modulus	Tensile Stress at Yield	Tensile Strain at Yield	Charpy Notched Impact Strength		Shore Hardness (Shore D)	Ball indentation hardness (H132/30)	Vicat Softening Temperature (B/50)		FNCT 6.0 MPa, 2% Arkopal, 50°C
		190°C, 2.16kg	190°C, 5kg				23 °	-30 °C					
Test Method	ISO 1183-1	ISO 1133-1		ISO 527-1, -2			ISO 179-1/1eA		ISO 868	ISO 2039-1	ISO 306	ISO 16770	
Unit	g/cm ³	g/10 min		MPa	MPa	%	kJ/m ²			MPa	°C	h	
High Density Polyethylene, <i>Hostalen</i>													
<i>Hostalen</i> GC 7260	0.960	8.0	23	1450	30	7	4.0	4.5	61	58	74	2.5	High stiffness, good impact resistance at low temperatures and optimum ESCR. Typical customer applications: crates, cartridges, caps & closures, toys & leisure products, housewares and panels & profiles
<i>Hostalen</i> GC 7260 LS	0.960	8.0	23	1450	30	7	4.0	4.5	61	58	74	2.5	Light-stabilized (UV) grade with high stiffness, good impact resistance at low temperatures and optimum ESCR. Typical customer applications: crates, toys & leisure products, housewares, panels & profiles and lids for dust bins
<i>Hostalen</i> GC 7258	0.958	7.5	22	1400	28	7	4.0	4.5	62	56	73	2.8	High stiffness combined with optimum ESCR, good impact resistance at low temperatures and low warpage. Typical customer applications: cartridges, caps & closures, crates, toys & leisure, housewares and panels & profiles
<i>Hostalen</i> GD 7255	0.955	4.0	11	1200	27	8	4.0	4.5	60	52	73	4.5	High impact resistance at low temperature, good stiffness and optimum ESCR. Typical customer applications: crates, caps & closures, toys & leisure products, housewares, panels & profiles and pallets
<i>Hostalen</i> GD 7255 LS	0.955	4.0	11	1200	27	8	4.0	4.5	60	52	73	4.5	Light-stabilized (UV) grade with high impact resistance at low temperatures, good stiffness and optimum ESCR. Typical customer applications: crates, caps & closures, toys & leisure products, panels & profiles, dust bins and pallets

ESCR = Environmental Stress Crack Resistance; FNCT = Full Notch Creep Test

You can find out more about us by visiting our website at: www.lyondellbasell.com

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT. LyondellBasell prohibits or restricts the use of its products in certain applications. For further information on restrictions or prohibitions of use, please contact a LyondellBasell representative. Users should review the applicable Safety Data Sheet before handling the product.

Hostalen and *Lupolen* are trademarks owned or used by LyondellBasell group companies. *Hostalen* is registered in the U.S. Patent and Trademark Office.

Polyethylene

Grades Used in Injection Molding Applications (2/2)

PROPERTIES	PHYSICAL			MECHANICAL						THERMAL	SPECIFIC CHARACTERISTICS AND TYPICAL CUSTOMER APPLICATIONS	
	Density 23°C	Melt Flow Rate		Tensile Modulus	Tensile Stress at Yield	Tensile Strain at Yield	Charpy notched impact strength		Shore Hardness (Shore D)	Ball indentation hardness (H132/30)		Vicat Softening Temperature (B/50)
		190°C, 2.16kg	190°C, 5kg				23 °	-30 °C				
Test Method	ISO 1183-1	ISO 1133-1		ISO 527-1,-2			ISO 179-1/1eA	ISO 868	ISO 2039-1	ISO 306		
Unit	g/cm ³	g/10 min		MPa	MPa	%	kJ/m ²			MPa	°C	
Low Density Polyethylene, Lupolen												
<i>Lupolen 1800 H</i>	0.919	1.5	-	200	9	NA	NA	NA	45	15	88	Low density, good flexibility, high impact and optimum ESCR. Typical applications: shoe insoles, pipe clamps, lids, car boot/trunk lining, brushes and champagne corks
<i>Lupolen 1800 P</i>	0.918	15	-	200	9	NA	NA	NA	45	12	80	Low density, good flexibility and high flowability. Other applications include use as a base resin for masterbatches and compounding
<i>Lupolen 1800 S</i>	0.917	20	-	160	8	NA	NA	NA	45	13	80	Low density, good flexibility and high flowability. Typical customer applications: ink cartridges, shoes and flippers for swimming, and brushes. Other applications include use as a base resin for masterbatches and compounding
<i>Lupolen 1800 U</i>	0.918	65	-	180	8	NA	NA	NA	45	12	75	Very high flowability with good balance of toughness, softness, dimensional stability and easy processability. Typical customer applications: consumer packaging and thin-wall injection molding. Other applications include use in masterbatches and as a viscosity modifier for compounds
<i>Lupolen 2420 K</i>	0.924	4	-	260	11	NA	NA	NA	48	18	92	Medium-flow LDPE with good impact resistance and optimum ESCR. Typical customer applications: collector trays for perforators, seals, bottle closures & packaging and safety traps in baby high chairs. Additional version (<i>Lupolen 2426K</i>) with slip agent available
<i>Lupolen 3020 K</i>	0.928	4	-	300	13	NA	NA	NA	51	21	97	Medium-flow LDPE with good stiffness and optimum ESCR. Typical customer applications: ink cartridges and hand grips. Additional version (<i>Lupolen 3026K</i>) with slip agent available

NA = Not Applicable

You can find out more about us by visiting our website at: www.lyondellbasell.com

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT. LyondellBasell prohibits or restricts the use of its products in certain applications. For further information on restrictions or prohibitions of use, please contact a LyondellBasell representative. Users should review the applicable Safety Data Sheet before handling the product.

Hostalen and *Lupolen* are trademarks owned or used by LyondellBasell group companies. *Hostalen* is registered in the U.S. Patent and Trademark Office.