

Polypropylene Consumer and Injection Molding

Containers, Crates, Garden Furniture, Housewares, Luggage, TSL, TWIM

TYPICAL PROPERTIES			MECHANICAL						THERMAL				OPTICAL	TYPICAL APPLICATIONS	SPECIFIC CHARACTERISTICS	
	Density	MFR 230°C, 2,16kg	Tensile Modulus	Tensile Stress at Yield	Tensile Elongation		Charpy Impact Notched			Ductile/Brittle Transition Temp.	Heat Deflection Temp. HDT/B	Vicat Softening Temp.				Haze 1mm
	23°C				at Yield	at Break	23 °C	0 °C	-20 °C			10N	50N			
Test Method	ISO 1183	ISO 1133-1	ISO 527	ISO 527	ISO 527	ISO 179/1eA			ISO 6603-2	0,45 MPa ISO 75-2	ISO 306/A50	ISO 306/B50	ASTM D1003			
Units	g/cm ³	g/10 min	MPa	MPa	%	kJ/m ²			°C	°C	°C		%			
GRADE NAME																
PP HOMOPOLYMER, <i>Moplen</i>																
<i>Moplen</i> HP500N	0.9	12	1400	35	10	>50	4				95	153	85		General purpose	Good flow with high stiffness, good creep resistance
<i>Moplen</i> HP400R	0.9	25	1350	32	10	>50	3				90	154	85		Garden furniture, housewares	High fluidity with good stiffness.
<i>Moplen</i> HP548R	0.9	23	1600	35	8	>50	2.7				95	154	94		Garden furniture, housewares	NU and AS.
<i>Moplen</i> HP648T	0.9	53	1600	35	8	>50	2				95	154	95		TWIM, housewares	NU and AS, high flow
PP RANDOM COPOLYMER, <i>Moplen</i>																
<i>Moplen</i> RP348R	0.9	25	1150	30	14	>50	6	2			80	130	72	9	TWIM, housewares, caps	NU and AS, high transparency and gloss
<i>Moplen</i> RP248R	0.9	30	900	22	10	>50	6.5	3.5			60	120	60	10	TWIM, housewares, TSL	NU and AS, high transparency and gloss
<i>Moplen</i> RP398T	0.9	40	1100	20	14	>50	5	2.5			70	127	70	9	TWIM, housewares, TSL	NU and AS, odorless, high transparency and gloss
<i>Moplen</i> RP390T	0.9	40	1100	28	14	>50	5	2.5			70	127	70	9	Co-Injection molding, TWIM, housewares	NU, odorless, high transparency and gloss
<i>Moplen</i> RP348T HP	0.9	48	1100	29	11	>50	4.5	2.5			70	130	72	9	TWIM, housewares, TSL	NU and AS, high transparency and gloss
<i>Moplen</i> RP248U	0.9	60	910	25	14	>50	5.9	2.5			69	125		11	TWIM, transparent housewares, TSL	NU and AS, excellent impact / aesthetics balance, high transparency, high flow
<i>Moplen</i> RP398U	0.9	71	1030	30	14	>50	5	1.5			70	130		11	Transparent packaging, housewares, TSL	NU and AS, odorless, high transparency and gloss, high flow
<i>Moplen</i> RP348U	0.9	75	1100	28	13	>50	4.5	1.5			80	130	72	11	TWIM, housewares, TSL	NU and AS, high transparency and gloss, high flow
<i>Moplen</i> RP398V	0.9	100	950	26	26	>50	5	2.5			70	127		10	Transparent packaging, reusable containers, housewares, TSL	NU and AS, high transparency and gloss, very high flow

Legend: NA=Not Applicable; NU=Nucleated; AS=Antistatic;
TWIM=Thin Wall Injection Molding; TSL=Toys,Sports and Leisure;
NB=No Break; IMR=Inter Material Replacement

You can find out more about us by visiting our website at: www.lyondellbasell.com
Before using a LyondellBasell product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the LyondellBasell product safely and legally. (Material Safety Data Sheets are available from LyondellBasell at www.lyondellbasell.com) This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. No one is authorized to make such warranties or assume any liabilities on behalf of LyondellBasell except in writing signed by an authorized LyondellBasell employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at LyondellBasell's option, and in no event shall LyondellBasell be liable for special, consequential, punitive, or exemplary damages.
Adflex, Adstif, Clyrell, Moplen are trademarks owned or used by LyondellBasell group companies.
Clyrell and *Moplen* are registered in the U.S. Patent and Trademark Office.

Polypropylene Consumer and Injection Molding

Containers, Crates, Garden Furniture, Housewares, Luggage, TSL, TWIM

TYPICAL PROPERTIES		MECHANICAL								THERMAL				OPTICAL	TYPICAL APPLICATIONS	SPECIFIC CHARACTERISTICS
Density	MFR 230°C, 2,16kg	Tensile Modulus	Tensile Stress at Yield	Tensile Elongation		Charpy Impact Notched			Ductile/Brittle Transition Temp.	Heat Deflection Temp. HDT/B	Vicat Softening Temp.		Haze 1mm			
				at Yield	at Break	23 °C	0 °C	-20 °C			10N	50N				
Test Method	ISO 1183	ISO 1133-1	ISO 527	ISO 527	ISO 527	ISO 179/1eA			ISO 6603-2	0,45 MPa ISO 75-2	ISO 306/A50	ISO 306/B50	ASTM D1003			
Units	g/cm ³	g/10 min	MPa	MPa	%	kJ/m ²			°C	°C	°C		%			
GRADE NAME																
PP HETEROPHASIC COPOLYMER, <i>Moplen</i>																
<i>Moplen</i> EP440G	0.9	1.3	1450	27	8	>50	40	10	7	<-50	78	150	66	Opaque	Luggage, TSL, crates	NU, excellent mechanical balance, excellent creep resistance
<i>Moplen</i> EP400H	0.9	1.7	1300	27	8	>50	30	10	7	<-50	78	153	70	Opaque	Luggage, TSL, crates	Excellent mechanical balance, excellent creep resistance
<i>Moplen</i> EP240H	0.9	2	1000	23	8	>50	80	12	8	<-50	75	148		Opaque	Crates	NU, excellent low temperature impact
<i>Moplen</i> EP340K	0.9	4	1100	20	5	>50	66	13	7	<-50	85	140		Opaque	Luggage, TSL, crates	NU, high impact
<i>Moplen</i> EP300K	0.9	4	1200	27	9	>50	13	5.5	4.5	-47	75	150		Opaque	Crates	Good impact
<i>Moplen</i> EP340M	0.9	7.5	1050	21	6	>50	45	9	7	<-50	80	144		Opaque	Luggage, TSL, crates	NU, high impact
<i>Moplen</i> EP540N	0.9	12	1500	28	5	>50	7	5	4		100	151		Opaque	Housewares, caps, TSL	NU
<i>Moplen</i> EP549P	0.9	15	1450				9	6.5	5.5	<-50				Opaque	Crates, hosewares	NU and AS, good stiffness/impact balance
<i>Moplen</i> EP240P	0.9	15	950	20	7	>50	20	9	5	<-50	78	142		Opaque	TWIM, TSL	NU, excellent low temperature impact
<i>Moplen</i> EP540P	0.9	15	1300	28	6	>50	7	4.5	3	-45	90	151		Opaque	Luggage, housewares, containers	NU, good stiffness/Impact balance
<i>Moplen</i> EP548P	0.9	16	1400	28	7	>50	8	6	3	-45	100	147	70	Opaque	TWIM, housewares, large to medium containers, crates	NU and AS, good stiffness/impact balance
<i>Moplen</i> EP548R	0.9	21	1500	27	5	>50	6	4.5	4	<-50				Opaque	TWIM, housewares, TSL	NU and AS, good stiffness/impact balance
<i>Moplen</i> EP249R	0.9	25	950				20	10	8	<-51				Opaque	Containers, crates	NU, high impact

Legend: NA=Not Applicable; NU=Nucleated; AS=Antistatic;
TWIM=Thin Wall Injection Molding; TSL=Toys,Sports and Leisure;
NB=No Break; IMR=Inter Material Replacement

You can find out more about us by visiting our website at: www.lyondellbasell.com
Before using a LyondellBasell product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the LyondellBasell product safely and legally. (Material Safety Data Sheets are available from LyondellBasell at www.lyondellbasell.com) This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. No one is authorized to make such warranties or assume any liabilities on behalf of LyondellBasell except in writing signed by an authorized LyondellBasell employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at LyondellBasell's option, and in no event shall LyondellBasell be liable for special, consequential, punitive, or exemplary damages.
Adflex, Adstif, Clyrell, Moplen are trademarks owned or used by LyondellBasell group companies.
Clyrell and *Moplen* are registered in the U.S. Patent and Trademark Office.

Polypropylene Consumer and Injection Molding

Containers, Crates, Garden Furniture, Housewares, Luggage, TSL, TWIM

TYPICAL PROPERTIES		MECHANICAL								THERMAL			OPTICAL	TYPICAL APPLICATIONS	SPECIFIC CHARACTERISTICS	
Density	MFR 230°C, 2,16kg	Tensile Modulus	Tensile Stress at Yield	Tensile Elongation		Charpy Impact Notched			Ductile/Brittle Transition Temp.	Heat Deflection Temp. HDT/B	Vicat Softening Temp.		Haze 1mm			
				at Yield	at Break	23 °C	0 °C	-20 °C			10N	50N				
Test Method	ISO 1183	ISO 1133-1	ISO 527	ISO 527	ISO 527	ISO 179/1eA			ISO 6603-2	0,45 MPa ISO 75-2	ISO 306/A50	ISO 306/B50	ASTM D1003			
Units	g/cm ³	g/10 min	MPa	MPa	%	kJ/m ²			°C	°C	°C		%			
GRADE NAME																
PP HETEROPHASIC COPOLYMER, <i>Moplen</i>																
<i>Moplen</i> EP448S	0.9	44	1400	27	5	>51	6	4	3	<-50	100	150		Opaque	Containers, housewares, toys, furniture, crates, pails	NU and AS, odorless, good stiffness/impact balance
<i>Moplen</i> EP548S	0.9	44	1550	28	5	30	5	3.5	3	<-50	95	151		Opaque	TWIM, housewares, TSL	NU and AS, good stiffness/impact balance
<i>Moplen</i> EP240T	0.9	48	950	19	5	>50	10	7	4		78	142		Opaque	TWIM, housewares	NU, high impact
<i>Moplen</i> EP448T	0.9	48	1250	27	5	40	5	3.5	2.5		90	151		Opaque	TWIM, housewares	NU and AS, good stiffness/impact balance
<i>Moplen</i> EP548T	0.9	48	1350	29	5	>50	4	2.5	2		98	152		Opaque	TWIM	NU and AS
<i>Moplen</i> EP348U	0.9	70	1200	24	4	30	5.5	4	3.2	-45	92	150	65	Opaque	TWIM, housewares	NU and AS, high flow, good impact
<i>Moplen</i> EP548U	0.9	70	1450	28	5	30	4	3.5	3	<-50	95	151		Opaque	TWIM, housewares	NU and AS, high flow
<i>Moplen</i> EP549U	0.9	70	1260	23	4	20	9	6	5	-45	98	147		Opaque	Packaging, housewares	NU and AS, Excellent impact/stiffness balance and fluidity
<i>Moplen</i> EP548V	0.9	100	1450	28	5	10	3.5	2.5	2	-45	90	152		Opaque	TWIM, housewares,TSL	NU and AS, very high flow
<i>Moplen</i> EP648V	0.9	100	1600	30	4	10	3.5	2	1		100	154		Opaque	TWIM, housewares	NU and AS,high rigidity, very high flow

Legend: NA=Not Applicable; NU=Nucleated; AS=Antistatic;
TWIM=Thin Wall Injection Molding; TSL=Toys,Sports and Leisure;
NB=No Break; IMR=Inter Material Replacement

You can find out more about us by visiting our website at: www.lyondellbasell.com
Before using a LyondellBasell product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the LyondellBasell product safely and legally. (Material Safety Data Sheets are available from LyondellBasell at www.lyondellbasell.com) This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. No one is authorized to make such warranties or assume any liabilities on behalf of LyondellBasell except in writing signed by an authorized LyondellBasell employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at LyondellBasell's option, and in no event shall LyondellBasell be liable for special, consequential, punitive, or exemplary damages.
Adflex, Adstif, Clyrell, , Moplen are trademarks owned or used by LyondellBasell group companies.
Clyrell and *Moplen* are registered in the U.S. Patent and Trademark Office.

Polypropylene Consumer and Injection Molding

Containers, Crates, Garden Furniture, Housewares, Luggage, TSL, TWIM



TYPICAL PROPERTIES			MECHANICAL						THERMAL				OPTICAL	TYPICAL APPLICATIONS	SPECIFIC CHARACTERISTICS	
	Density	MFR	Tensile Modulus	Tensile Stress at Yield	Tensile Elongation		Charpy Impact Notched			Ductile/Brittle Transition Temp.	Heat Deflection Temp. HDT/B	Vicat Softening Temp.				Haze 1mm
	23°C	230°C, 2,16kg			at Yield	at Break	23 °C	0 °C	-20 °C			10N	50N			
Test Method	ISO 1183	ISO 1133-1	ISO 527	ISO 527	ISO 527	ISO 179/1eA			ISO 6603-2	0,45 MPa ISO 75-2	ISO 306/A50	ISO 306/B50	ASTM D1003			
Units	g/cm ³	g/10 min	MPa	MPa	%	kJ/m ²			°C	°C	°C		%			
GRADE NAME																
Clyrell																
Clyrell EC348P	0.9	14	1200	28	13	>50	5	2	1	-5	75	128		15	Transparent shock resistant food/non food containers, housewares	NU, high gloss
Clyrell EC340Q	0.9	20	1150	23	13	>50	22	5.5	4	-46	88	127		38	TWIM,TSL	NU, high gloss
Clyrell EC340R	0.9	26	1180	23	12	>50	6.5	3.5	2	-48	90	123		32	Food containers	NU, good impact and low stress whitening
Clyrell EC140R	0.9	30	900	20	18	>50	10	6	4	-50	60	114		20	Food containers	NU, very high impact, high flow, low stress whitening
Clyrell EC390T	0.9	45	1150	23	13	>50	6	4	3	<-50				30	Food containers	NU, good impact and low stress whitening
Clyrell RC449S	0.9	40	1250	30	11	>50	4.2	1.5			75			5.5	Transparent food packaging, housewares, consumer goods, cosmetics	NU, AS, excellent transparency and gloss, improved stiffness with good impact, very good organoleptic
Clyrell RC549S	0.9	40	1470	34	10	>50	3	1.2			86			10	Transparent food packaging, transparent drinking cups, housewares, consumer goods, cosmetics	NU, AS, very high stiffness, very good transparency, gloss and organoleptic
HOMOPOLYMER-Adstif																
Adstif HA840R	0.9	20	2300	41	6	12	2				110	158		50	TWIM, garden furniture	NU, good dimensional stability at high temperature
PP HETEROPHASIC COPOLYMER-Adstif																
Adstif EA648P	0.9	18	1700	32	5	50	6.5	3	2.5		100	153		Opaque	TWIM, dairy products, housewares	NU, AS, High crystallinity
Adflex																
Adflex C200F	0.88	6	200	8	30	600	NB	80	65	<-50	41	80	-	48	Containers, housewares	Soft touch, impact modifier for transparent applications
Adflex X500F	0.89	7.5	550	14	20	700	NB	79	45	<-50	58	94	-	23	Containers, housewares	Impact modifier for transparent applications, low temperature exposure
Adflex X100G	0.88	8	80	NA	NA	450	NB	NB	NB	<-50	40	56	-	-	Containers, housewares	Soft touch, impact modifier for higher melt flow rate
Adflex Z101H	0.88	27	80	NA	NA	400	NB	NB	92	<-50	40	55	-	-	Containers, housewares	Soft touch, impact modifier for higher melt flow rate

Legend: NA=Not Applicable; NU=Nucleated; AS=Antistatic; TWIM=Thin Wall Injection Molding; TSL=Toys,Sports and Leisure; NB=No Break; IMR=Inter Material Replacement

You can find out more about us by visiting our website at: www.lyondellbasell.com

Before using a LyondellBasell product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the LyondellBasell product safely and legally. (Material Safety Data Sheets are available from LyondellBasell at www.lyondellbasell.com) This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. No one is authorized to make such warranties or assume any liabilities on behalf of LyondellBasell except in writing signed by an authorized LyondellBasell employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at LyondellBasell's option, and in no event shall LyondellBasell be liable for special, consequential, punitive, or exemplary damages. Adflex, Adstif, Clyrell, Moplen are trademarks owned or used by LyondellBasell group companies. Clyrell and Moplen are registered in the U.S. Patent and Trademark Office.

Quality Circular Polymers

Containers, Crates, Garden Furniture, Luggage, TWIM



TYPICAL PROPERTIES		MECHANICAL						ADDITIONAL INFO			TYPICAL APPLICATIONS	SPECIFIC CHARACTERISTICS			
		Density	MFR 230°C, 2,16kg	Tensile Modulus	Tensile Stress at Yield	Tensile Elongation at Break	Flexural Modulus	Charpy Impact Notched							
Test Method	ISO 1183	ISO 1133-1	ISO 527	ISO 527	ISO 527	ISO 527	23 °C	0 °C	-20 °C	COLOR	RECYCLED PC %	RESTRICTION	TYPICAL APPLICATIONS	SPECIFIC CHARACTERISTICS	
Units	g/cm ³	g/10 min	MPa	MPa	%	MPa	kJ/m ²								
PP HETEROPHASIC COPOLYMER, QCP															
Moplen	QCP840P	1,050	12	2250	27	60	2100	4.0			Grey	>75%	See disclaimer below	Containers, crates, furniture, pails, bin dividers	High stiffness, 20% Talc filled
Moplen	QCP840P Black	1,060	14	2300	27	15	2300	4.0			Black	>75%	See disclaimer below	Containers, crates, furniture, pails, bin dividers	High stiffness, 20% Talc filled
Moplen	QCP249P	0.935	15	1100	22	150	1090	10.5			Grey	>80%	See disclaimer below	Containers, crates, furniture, pails, baby strollers	NU, High impact resistance
Moplen	QCP249P Ivory	0.935	15	1100	22	150	1090	10.5			Ivory	>80%	See disclaimer below	Containers, crates, furniture, pails	NU, High impact resistance
Moplen	QCP249P Black	0.935	15	1100	22	150	1090	10.5			Black	>80%	See disclaimer below	Containers, crates, furniture, pails, baby strollers	NU, High impact resistance
Moplen	QCP189P	0.918	15	800	19	30	800	30		>7	Grey	>85%	See disclaimer below	High impact containers, luggage, furniture	AS, Very high impact even at low temperature
Moplen	QCP300P	0.915	16	1300	27	40	1200	6.5			Grey	>95%	See disclaimer below	Containers, pails, crates, furniture, caps	Medium fluidity
Moplen	QCP300P Ivory	0.915	16	1300	27	40	1200	6.5			Ivory	>95%	See disclaimer below	Containers, pails, crates, furniture, caps	
Moplen	QCP300P Black	0.917	16	1200	27	50	1150	6.0			Black	>95%	See disclaimer below	Containers, pails, crates, furniture, caps	Medium fluidity
Moplen	QCP300R	0.915	21	1250	26	30	1150	6.5			Grey	>95%	See disclaimer below	Containers, pails, crates, furniture, caps	Medium fluidity
Moplen	QCP300R Ivory	0.915	21	1250	26	30	1150	6.5			Ivory	>95%	See disclaimer below	Containers, pails, crates, furniture, caps	
Moplen	QCP300R Black	0.914	20	1200	27	25	1150	5.5			Black	>95%	See disclaimer below	Containers, pails, crates, furniture, caps	Medium fluidity
Moplen	QCP300S	0.915	35	1150	26	25	1100	6.0			Grey	>95%	See disclaimer below	Crates, boxes, pallets, pails, compounds, caps	Good fluidity
Moplen	QCP300S Ivory	0.915	35	1150	26	25	1100	6.0			Grey	>95%	See disclaimer below	Crates, boxes, pallets, pails, compounds, caps	Good fluidity
Moplen	QCP300S Black	0.916	35	1150	26	25	1050	6.0			Black	>95%	See disclaimer below	Crates, boxes, pallets, pails, compounds, caps	Good fluidity
Moplen	QCP540S	0.950	35	1400	24	25	1300	6.0			Grey	>85%	See disclaimer below	Crates, boxes, pallets, pails, compounds, caps	NU, Good fluidity
Moplen	QCP540S Black	0.950	35	1400	24	25	1300	6.0			Black	>85%	See disclaimer below	Crates, boxes, pallets, pails, compounds, caps	NU, Good fluidity
Moplen	QCP840S	1,050	40	2075	25	<10	2180	3.0			Grey	>75%	See disclaimer below	High stiffness containers	Good fluidity, high stiffness, 20% Talc filled
Moplen	QCP840S Black	1,050	40	2075	25	<10	2180	3.0			Black	>75%	See disclaimer below	High stiffness containers	Good fluidity, high stiffness, 20% Talc filled
Moplen	QCP300T	0.915	50	1150	26	20	1100	6.0			Grey	>95%	See disclaimer below	Large containers, boxes, compounds	High fluidity
Moplen	QCP300T Black	0.915	50	1150	26	20	1100	6.0			Black	>95%	See disclaimer below	Large containers, boxes, compounds	High fluidity
Moplen	QCP300U	0.915	70	1250	26	10	1150	5.0			Grey	>95%	See disclaimer below	Large containers, boxes, DVD boxes, compounds	Very high fluidity
Moplen	QCP300U Ivory	0.915	70	1250	26	10	1150	5.0			Ivory	>95%	See disclaimer below	Large containers, boxes, DVD boxes, compounds	Very high fluidity
Moplen	QCP300U Black	0.915	70	1150	25	10	1050	4.5			Black	>95%	See disclaimer below	Large containers, boxes, DVD boxes, compounds	Very high fluidity

*Restrictions: this product is not intended for highly regulated applications including food contact, potable water contact, medical and pharmaceutical applications.

Legend: NA=Not Applicable; NU=Nucleated;
AS=Antistatic; TWIM=Thin Wall Injection Molding;
TSL=Toys, Sports and Leisure;
NB=No Break; IMR=Inter Material Replacement

You can find out more about us by visiting our website at: www.lyondellbasell.com

Before using a LyondellBasell product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the LyondellBasell product safely and legally. (Material Safety Data Sheets are available from LyondellBasell at www.lyondellbasell.com) This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. No one is authorized to make such warranties or assume any liabilities on behalf of LyondellBasell except in writing signed by an authorized LyondellBasell employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at LyondellBasell's option, and in no event shall LyondellBasell be liable for special, consequential, punitive, or exemplary damages.

Adflex, Adstif, Clyrell, Moplen are trademarks owned or used by LyondellBasell group companies. Clyrell and Moplen are registered in the U.S. Patent and Trademark Office.