

Pipe & Industrial Sheet: *Hostalen* HDPE and *Petrothene* HDPE

1/4

Properties	Physical			Mechanical					Thermal	Other		Specific characteristics	Typical customer applications
	MFR 190 °C/ 5 kg	MFR 190 °C/ 21.6 kg	Density	Tensile modulus (sec., v=1mm/min)	Tensile Stress at Yield (v=50mm/min)	Hardness shore D (3 sec.)	Charpy notched impact strength		Vicat softening point (49 N)	OIT (210 °C)	FNCT (4 MPa, 2% Arcopal, 80 °C)		
TEST METHOD	ISO 1133-1		ISO 1183 A	ISO 527	ISO 527	ISO 868	at 23 °C	at -30 °C	ISO 306/B	ISO11357-6	ISO 16770		
UNITS	g/10 min	g/10 min	g/cm ³	MPa	MPa		kJ/m ²		°C	min	h		
Product Grades – HOSTALEN													
GM 5010 T3 Black	0.43	9.0	0.957	1050	22	59	24	8	70	30	>100	High impact, stiffness; HDPE; PE80 black color (RAL 9004); pellets	Pressure pipes (sewage); gas pipes; drinking water pipes; relinings; linings; sewage p.; corrugated p.; industrial pipes
CRP 100 Black	0.23	6.4	0.959	1100	23	63	26	13	74	30	>1000	High impact, stiffness; HDPE; PE100 black color (RAL 9004); pellets	Pressure pipes (sewage); gas pipes; drinking water pipes; relinings; fittings; industrial pipes
CRP 100 RESIST CR Black	0.23	6.4	0.958	1100	23	63	26	13	74	30	>8760	Superior ESCR; PE100-RC, black color (RAL9004); fulfills PAS1075; pellets	Pressure pipes for sandless bedding; no dig installation; relining
CRP 100 Black (XL)	0.23	6.4	0.959	1100	23	63	26	13	74	30	>1000	High impact, stiffness; high melt viscosity; low sagging; PE 100 black color (RAL9004)	Extra large bore and thick-walled pressure pipes
CRP 100 RD Black	0.23	6.4	0.959	1100	23	63	26	13	74	30	>1000	Improved resistance against disinfectants; PE 100 black color (RAL9004); pellets	Drinking water pipes; industrial pipes; fittings
CRP 100 RT Black	0.45	9.5	0.957	1050	22	59	24	8	70	40	350	Excellent heat ageing and extremely high extraction stability, PE-RT, black color (RAL9004)	Industrial applications at higher temperatures >40°C, where long term heat ageing stability is required
CRP 100 W Blue	0.27	7.6	0.950	1050	23	62	26	13	74	30	>1000	Improved processability; High impact, stiffness; PE 100 dark blue color (similar RAL 5005); pellets	Drinking water pipes; relining
CRP 100 RESIST CR W Blue	0.27	7.3	0.950	1050	23	63	26	13	74	30	>8760	Superior ESCR; PE100-RC, dark blue color (similar RAL 5005); fulfills PAS1075; pellets	Drinking water pipes for sandless bedding, no dig installation and relining
CRP 100 RESIST CR Orange	0.27	7.3	0.950	1050	23	62	29	15	74	30	>8760	Superior ESCR; PE100-RC, orange color (similar RAL 1033); fulfills PAS1075; pellets	Gas pipes for sandless bedding, no dig installation and relining
CRP 100 Orange	0.23	6.4	0.951	1050	23	62	29	15	74	30	>1000	PE100, good ESCR, orange color (similar RAL 1033)	Gas pipes acc. EN1555 / ISO 4437
GM 9310 C Black		4.5	1.000	1250	26	66	5	3	83	20		Semiconductive; HDPE; black color (RAL9004); pellets	Pipes and sheets with lower surface resistivity for explosion-proof areas
Product Grades – PETROTHENE													
KR52828E	1.1	21	0.956	900	23	61				30	40	HDPE, black color, good weather resistance, good heat ageing resistance	Jacketing of wire & cable, pressureless sewage pipes, cable conduits, microducts, extruded sheets, injection molded fittings
LR52800E	1.1	21	0.950	900	23	61				30	40	HDPE, natural color, good heat ageing resistance	Jacketing of wire & cable, pressureless sewage pipes, cable conduits, microducts, extruded sheets, injection molded fittings

You can find out more about us by visiting our website at: www.lyb.com

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT. LyondellBasell prohibits or restricts the use of its products in certain applications. For further information on restrictions or prohibitions of use, please contact a LyondellBasell representative.

Users should review the applicable Safety Data Sheet before handling the product. PB-1 may not be used in the manufacture of pipe applications intended for sale or shipment to North America, without prior written approval by Seller for each specific product and application.

Akoalit, Akoalfloor, Hifax, Hostalen, Lucalen, Lupolen and Moplen are trademarks owned or used by one of the LyondellBasell family of companies and are registered in the U.S. Patent and trademark Office.

Pipe & Industrial Sheet: Crosslinkable HDPE and PE-RT

2/4

Properties	Physical				Mechanical				Thermal		Specific Characteristics	Typical Customer Applications
	MFR 190 °C/ 2.16 kg	MFR 190 °C/ 5 kg	MFR 190 °C/ 21.6 kg	Density	Tensile modulus (sec., v=1mm/min)	Tensile Stress at Yield (v=50mm/ min)	Hardness shore D (3 sec.)	Ball indentation hardness H132/30	Vicat softening point (9.8 N)	Vicat softening point (49 N)		
TEST METHOD	ISO 1133-1			ISO 1183 A	ISO 527	ISO 527	ISO 868	ISO 2039-1	ISO 306/A	ISO 306/B		
UNITS	g/10 min	g/10 min	g/10 min	g/cm ³	MPa	MPa		MPa	°C	°C		
Product Grades – LUPOLEN												
4261A Q416		0.5	8.5	0.946	850	24	62	40	125	75	x-linkable (Radiation); PE-Xc; HDPE; color natural; pellets	Heating; plumbing; multilayer pipes
5261Z Q456			2.0	0.954	1100	27	65	52	132	80	x-linkable (Peroxide); PE-Xa; HDPE; color natural; powder	Heating; plumbing; large bore pipes for gas/water; compression-molded sheets
5261Z Q456 B			3.0	0.954	1200	27	65	52	132	80	x-linkable (Peroxide); PE-Xa; HDPE; color natural; powder	Heating; plumbing; multilayer pipes
5461B Q471		0.5	10.0	0.953	1100	28	64	49	130	79	x-linkable (Peroxide); PE-Xa; HDPE; color natural; powder	Heating; plumbing; multilayer pipes
5461B Q471 B		0.7	15.0	0.953	1100	28	64	49	130	79	x-linkable (Peroxide); PE-Xa; HDPE; color natural; powder; lower viscosity than 5461B Q471	Heating; plumbing; multilayer pipes
Product Grades – HOSTALEN												
4731B		0.45	9.5	0.947	850	22	59		128	70	PE-RT Type II; PE 100; color natural; pellets; good processability, extremely high resistance to ageing	Heating; plumbing; multilayer pipes
4131B		2.2	18	0.941	650	23	58		125	70	PE-RT Type II with higher flexibility; color natural; pellets; good processability, extremely high resistance to ageing	Underfloor heating; plumbing; multilayer pipes

You can find out more about us by visiting our website at: www.lyb.com

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT. LyondellBasell prohibits or restricts the use of its products in certain applications. For further information on restrictions or prohibitions of use, please contact a LyondellBasell representative.

Users should review the applicable Safety Data Sheet before handling the product. PB-1 may not be used in the manufacture of pipe applications intended for sale or shipment to North America, without prior written approval by Seller for each specific product and application.

Akoalit, Akoafloor, Hifax, Hostalen, Lucalen, Lupolen and Moplen are trademarks owned or used by one of the LyondellBasell family of companies and are registered in the U.S. Patent and trademark Office.

Pipe & Industrial Sheet: *Hostalen* PP

3/4

Properties	Physical		Mechanical					Thermal		Specific Characteristics	Type	Color	Typical customer applications
	MFR 230 °C/ 2.16 kg	MFR 230 °C/ 5 kg	Tensile modulus (sec., v=1mm/ min)	Tensile Stress at Yield (v=50mm/ min)	Tensile Strain at Yield (v=50mm/ min)	Notched Charpy Impact			Vicat softening point A				
TEST METHOD	ISO 1133	ISO 1133	ISO 527-2	ISO 527-2	ISO 527-2	ISO 179/1eA			ISO 306/A				
UNITS	g/10 min	g/10 min	MPa	MPa	%	kJ/m ²			°C				
Product Grades – HOSTALEN PP													
H2150	0.3	1.5	1500	36	11	30	4.3	–	158	High heat and extraction stability	PP-H	natural	Pipes; sheets; rods; fittings; profiles; punching boards; filterplates; blow molded parts
H2150 304850	0.3	1.3	1500	36	10	38	5	–	156	High heat and extraction stability	PP-H	grey (RAL 7032)	Pipes; sheets; rods; fittings; profiles; punching boards; filterplates; blow molded parts
H2150-RC	0.3	1.3	1400	36	10	61	6	–	–	High heat and extraction stability	PP-H	natural	Pipes; sheets; rods; fittings; profiles; punching boards; filterplates; blow molded parts; classified by ISO9080 as PP100
H2450	0.3	1.3	1450	36	11	20	5	–	157	High heat and extraction stability; non-nucleated	PP-H	natural	Pipes; sheets; rods; fittings; profiles; punching boards; filterplates; blow molded parts
H2250 36	0.3	1.3	1500	36	12	26	6	–	157	High heat and extremely high extraction stability	PP-H	grey (RAL 7032)	Press. pipes; sheets; rods; housings; filterplates; fittings
H7350FLS 303064	0.4	2.0	1500	35	11	18	5	–	158	Flame retardant; not food approved	PP-H	grey (RAL 7037)	House drain-pipes; semifinished products
EPD60R	0.4	1.6	1100	26	15	54	18	3.5	151	Exc. impact strength; long-term heat & detergent resistance	PP-B	natural	Sheets; corrugated hoses; industrial pipes; conduits; profiles
H2464	0.3	1.3	1350	28	13	55	34	5	155	Excellent balance rigidity/impact; dimesional stability	PP-B	natural	Sewage/drainage pipes (EN1852/EN13476) profiles; blown and injection molded parts
H2483	0.3	1.3	1800	32	8	67	20	4.3	159	High stiffness, high impact; dimensional stability;	PP-B	natural	Sewage/drainage pipes (EN1852/EN13476) profiles; blown and injection molded parts
H2992	0.25	1.3	2000	38	8	50	4	2.5	–	Very high stiffness; impact; dimensional stability	PP-B	natural	Sewage/drainage pipes (EN1852/EN13476) profiles; blown and injection molded parts
H1022	0.3	1.3	1300	30	13	50	15	3	159	Basic stabilization; good heat aging resistance	PP-B	natural	Pipes; fittings; sheets; profiles; blow molded parts
H1022 12	0.25	1.3	1400	31	12	117	21	4	158	Basic stabilization; good heat aging resistance	PP-B	black	Pipes; fittings; sheets; profiles; blow molded parts
H2222 36	0.3	1.3	1350	30	12	50	13	5.8	158	High heat stability; extreme extraction stability	PP-B	grey (RAL 7032)	Press. pipes; sheets; profiles; filterplates; fittings
H2142 12	0.3	1.4	1500	34	12	54	5	2	150	High heat stability; weather resistance; low creep	PP-B	black	Mechanical-joint compression fittings (ISO14236); classified by ISO9080 as PP100
H4122 103220	0.3	1.3	1400	30	13	110	20	5.8	159	High heat, weather and extreme extraction stability	PP-B	black	Pipes; solar heat absorbers; corrugated pipes; fittings
XN125-P	0.2	1.1	850	26	12	–	8.0	–	–	High heat stability; extreme extraction stability	PP-RCT	natural	Press. pipes (EN ISO15874); hot/cold water pipes; sheets and parts in chemical apparatus; classified by ISO9080 as PP125/PP-RCT
XN112-I	0.2	1.1	800	24	32	–	9.5	–	–	High heat stability; extreme extraction stability	PP-RCT	natural	Press. pipes (EN ISO15874); hot/cold water pipes; sheets and parts in chemical apparatus; classified by ISO9080 as PP112/PP-RCT
H5416	0.3	1.3	850	24	13	89	12.0	–	132	High heat stability; extreme extraction stability; good impact	PP-R	natural	Press. pipes (EN ISO15874); hot/cold water pipes; sheets and parts in chem. apparatus; classified by ISO9080 as PP100

You can find out more about us by visiting our website at: www.lyb.com

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT. LyondellBasell prohibits or restricts the use of its products in certain applications. For further information on restrictions or prohibitions of use, please contact a LyondellBasell representative.

Users should review the applicable Safety Data Sheet before handling the product. PB-1 may not be used in the manufacture of pipe applications intended for sale or shipment to North America, without prior written approval by Seller for each specific product and application.

Akoalit, Akoafloor, Hifax, Hostalen, Lucalen, Lupolen and Moplen are trademarks owned or used by one of the LyondellBasell family of companies and are registered in the U.S. Patent and trademark Office.

Pipe and Industrial sheet: Polybutene-1

4/4

Properties	Physical		Mechanical				Thermal	Color	Specific Characteristics	Typical Customer Applications
	MFR 190 °C/2.16kg	Density	Flexural Modulus	Tensile Stress at Yield	Tensile Stress at Break	Tensile Strain at Break	Melting Temperature			
	Test Method	ISO 1133-1	ISO 1183	ISO 178	ISO 527	ISO 527	ISO 527			
Unit	g/10 min	g/cm ³	MPa	MPa	MPa	%	°C			
Product Grades										
<i>Akoafloor</i> PB R 509 Brown	0.7	0.93	370	15	35	300	124–126	Brown	Random copolymer	Underfloor heating
<i>Akoafloor</i> PB R509	0.7	0.92	370	15	35	300	124–125	Natural	Random copolymer	Pressure pipe, not for potable water
<i>Akoafloor</i> PB 4235-1 Ivory	0.6	0.93	450	17	30	225	127–129	Ivory	Homopolymer	Non-potable heating water
<i>Akoalit</i> PB 4267 Grey	0.6	0.925	450	17	30	225	127–129	Grey	Homopolymer	High-performance extrusion into pipe for potable hot and cold water distribution applications where improved organoleptic properties are required
<i>Akoalit</i> PB 4268 White	0.6	0.925	450	17	30	225	127–129	White	Homopolymer	High-performance extrusion into pipe for potable hot and cold water distribution applications where improved organoleptic properties are required
<i>Akoalit</i> PB DKG 300	2.0	1.325	6000	75	72	4.5	127–129	Natural	Homopolymer	Glass fibre reinforced high flow polybutene-1, typically used for fitting applications such as fitting bodies, support rings, etc. in combination with hot and cold potable water pipe installations

You can find out more about us by visiting our website at: www.lyb.com

Before using a product sold by a company of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY WARRANTY) OTHER THAN AS SEPARATELY AGREED TO BY THE PARTIES IN A CONTRACT. LyondellBasell prohibits or restricts the use of its products in certain applications. For further information on restrictions or prohibitions of use, please contact a LyondellBasell representative.

Users should review the applicable Safety Data Sheet before handling the product. PB-1 may not be used in the manufacture of pipe applications intended for sale or shipment to North America, without prior written approval by Seller for each specific product and application.

Akoalit, *Akoafloor*, *Hifax*, *Hostalen*, *Lucalen*, *Lupolen* and *Moplen* are trademarks owned or used by one of the LyondellBasell family of companies and are registered in the U.S. Patent and trademark Office.