

Appliance materials selector guide

Product	Description	Suggested Applications	Specific Gravity ASTM D 792	Tensile Yield ASTM D 638		Tensile Break ASTM D 638	
				Elongation %	Stress MPa (psi)	Elongation %	Stress MPa (psi)
DURASTAR™ Polymers							
DS1010 Clear and Tints	PCTA	Refrigerator interior parts	1.20	5	47 (6,900)	300	51 (7,400)
DS2010 Clear and Tints		Floor care	1.20	5	46 (6,700)	310	53 (7,700)
DS1910HF Clear and Tints		Washing machine lids	1.19	5	50 (7,200)	270	43 (6,300)
EASTAR™ Copolyesters							
DN011 Clear	PCTG	Refrigerator interior parts Floor care	1.23	4	44 (6,300)	330	54 (7,800)
EN067 Clear and Tints	PET		1.32	4	57 (8,200)	134	24 (3,500)
GN007 Clear and Tints	PETG		1.27	4.4	50 (7,200)	180	30 (4,300)
TENITE™ Cellulosics							
Propionate 375-12 — 12% PZ Clear and Tints	Cellulose acetate propionate	Floor care	1.20	45	31.7 (4,600)	45	31 (4,800)
TRITAN™ Copolyesters							
TX 1000	Copolyester	Small appliances Dryer doors	1.18	6	43 (6,200)	210	53 (7,700)
TX 1001 (Mold Release)							
TX 1501 HF (High Flow)			1.18	7	43 (6,200)	210	52 (7,500)
TX 2000			1.17	7	44 (6,400)	140	53 (7,700)
TX 2001 (Mold Release)							

^aNonbreak as defined by ASTM D 256 using 3.2-mm (1/8-in.) specimens.

Unless noted otherwise, all tests are run @ 23°C (73°F) and 50% relative humidity. Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Conversions of metric/U.S. customary values may have been rounded off and therefore may not be exact conversions.

Product	Flexural Modulus MPa (105 psi) ASTM D 790	Izod Impact, Notched J/m (ft·lbf/in.) @ 23°C (73°F) ASTM D 256	Deflection Temperature °C (°F) ASTM D 648		Optical Properties ASTM D 1003	
			@ 1.82 MPa (264 psi)	@ 0.455 MPa (66 psi)	Transmittance %	Haze %
DURASTAR™ Polymers						
DS1010 Clear and Tints	2,000 (2.9)	80 (1.5)	65 (149)	75 (167)	91	0.3
DS2010 Clear and Tints	1,900 (2.8)	370 (7.0)	65 (149)	73 (164)	91	0.3
DS1910HF Clear and Tints	1,900 (2.7)	80 (1.5)	66 (150)	73 (163)	92	<1
EASTAR™ Copolyesters						
DN011 Clear	1,800 (2.6)	NB ^a	64 (147)	73 (163)	92	<0.1
EN067 Clear and Tints	2,600 (3.8)	58 (1.1)	61 (142)	66 (151)	84	—
GN007 Clear and Tints	2,100 (3.0)	105 (1.9)	62 (143)	70 (158)	90	0.2
TENITE™ Cellulosics						
Propionate 375-12 — 12% PZ Clear and Tints	1,448 (2.1)	416 (7.8)	75 (167)	83 (181)	<90	<8.5
TRITAN™ Copolyesters						
TX 1000	1,550 (2.3)	980 (18.4)	85 (185)	99 (210)	90	<1
TX 1001 (Mold Release)						
TX 1501 HF (High Flow)	1,575 (2.3)	860 (16.1)	81 (178)	94 (201)	91	<1
TX 2000	1,585 (2.3)	650 (12.2)	92 (198)	109 (228)	92	<1
TX 2001 (Mold Release)						

EASTMAN

Eastman Chemical Company Corporate Headquarters

P.O. Box 431
Kingsport, TN 37662-5280 U.S.A.

Telephone:
U.S.A. and Canada, 800-EASTMAN
(800-327-8626)
Other Locations, (1) 423-229-2000
Fax: (1) 423-229-1193

Eastman Chemical Latin America

9155 South Dadeland Blvd.
Suite 1116
Miami, FL 33156 U.S.A.

Telephone: (1) 305-671-2800
Fax: (1) 305-671-2805

Eastman Chemical B.V.

Fascinatio Boulevard 602-614
2909 VA Capelle aan den IJssel
The Netherlands

Telephone: (31) 10 2402 111
Fax: (31) 10 2402 100

Eastman (Shanghai) Chemical Commercial Company, Ltd. Jingan Branch

1206, CITIC Square
No. 1168 Nanjing Road (W)
Shanghai 200041, P.R. China

Telephone: (86) 21 6120-8700
Fax: (86) 21 5213-5255

Eastman Chemical Japan, Ltd.

AIG Aoyama Building 5F
2-11-16 Minami Aoyama
Minato-ku, Tokyo 107-0062 Japan

Telephone: (81) 3-3475-9510
Fax: (81) 3-3475-9515

Eastman Chemical Asia Pacific Pte. Ltd.

#05-04 Winsland House
3 Killiney Road
Singapore 239519

Telephone: (65) 6831-3100
Fax: (65) 6732-4930

www.eastman.com

Material Safety Data Sheets providing safety precautions, that should be observed when handling and storing Eastman products, are available online or by request. You should obtain and review the available material safety information before handling any of these products. If any materials mentioned are not Eastman products, appropriate industrial hygiene and other safety precautions recommended by their manufacturers should be observed.

Neither Eastman Chemical Company nor its marketing affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment and for the health and safety of your employees and purchasers of your products. NO WARRANTY IS MADE OF THE MERCHANTABILITY OR FITNESS OF ANY PRODUCT, AND NOTHING HEREIN WAIVES ANY OF THE SELLER'S CONDITIONS OF SALE.

DuraStar, Eastar, Eastman, Tenite and Tritan are trademarks of Eastman Chemical Company.

© Eastman Chemical Company, 2008.