INEOS Styrolution

Terluran® GP-22

ABS

INEOS Styrolution

Terluran® GP-22 is an easy-flow, general purpose injection molding grade with high resistance to impact and heat distortion; intended for a wide range of applications, particularly in the housings sector.

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	19	cm³/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2300	MPa	ISO 527
Yield stress	45	MPa	ISO 527
Yield strain	2.6	%	ISO 527
Nominal strain at break	10	%	ISO 527
Impact Strength (Charpy), +23°C	180	kJ/m²	ISO 179/1eU
Impact Strength (Charpy), -30°C	100	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	22	kJ/m²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	8	kJ/m²	ISO 179/1eA

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (1.80 MPa)	94	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	99	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	96	°C	ISO 306
Burning Behav. at 1.5 mm Nom. Thickn.	HB	class	UL 94
Thickness tested	1.5	mm	-
UL recognition	yes	-	-
Burning Behav. at thickness h	HB	class	UL 94
Thickness tested	3.0	mm	-
UL recognition	yes	-	-

Electrical Properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 100Hz	2.9	-	IEC 62631-2-1
Relative permittivity, 1MHz	2.8	-	IEC 62631-2-1
Dissipation Factor, 100Hz	48	E-4	IEC 62631-2-1
Dissipation Factor, 1MHz	79	E-4	IEC 62631-2-1
Volume Resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface Resistivity	1E13	Ohm	IEC 62631-3-2

Other Properties	Value	Unit	Test Standard
ISO Data			
Water Absorption	1	%	Sim. to ISO 62
Humidity absorption	0.22	%	Sim. to ISO 62
Density	1040	kg/m³	ISO 1183

Rheological calculation properties	Value	Unit	Test Standard
ISO Data			
Density of melt	927	kg/m³	-
Thermal Conductivity of Melt	0.202	W/(m K)	-
Spec. heat capacity of melt	2570	J/(kg K)	-
Ejection temperature	91	°C	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	220 - 260	°C	-
Mold temperature	30 - 60	°C	-

Diagrams

Viscosity-shear rate



Shearstress-shear rate



Dynamic Shear modulus-temperature



Stress-strain



Secant modulus-strain



Stress-strain (isochronous) 23 °C



Creep modulus-time 23 °C



Stress-strain (isochronous) 60 °C



Creep modulus-time 60 °C



Specific volume-temperature (pvT)



Tensile Modulus-Temperature



Characteristics

Processing
Injection Molding

Special Characteristics
Platable, Impact modified, Heat aging stabilized

Delivery form
Pellets

Injection Molding

PREPROCESSING
Pre-drying, Temperature: 80 °C
Pre-drying, Time: 2 - 4h
PROCESSING
Melt temperature, range: 220 - 260 °C
Mold temperature, range: 30 - 80 °C

Disclaimer

Liability Exclusion
These guide values are measured and provided by the product manufacturer and have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions. M-Base has taken the guide values from the producer's original Technical Data Sheet. **ALBIS AND M-BASE ARE THEREFORE NOT RESPONSIBLE FOR THE ACCURACY OF THE GUIDE VALUES AND CANNOT GIVE ANY WARRANTY WITH REGARD TO THEIR CORRECTNESS.**

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

Healthcare uses: the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.
Important: irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.

 Copyright Altair Engineering GmbH.